

This Page Is Inserted by IFW Operations  
and is not a part of the Official Record

## **BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning documents *will not* correct images,  
please do not report the images to the  
Image Problem Mailbox.**



Home



Search



List

☐ Include**MicroPatent® PatSearch FullText:** Record 1 of 1

Search scope: US Granted US Applications EP-A EP-B WO JP (bibliographic data only) DE-C DE-A  
DE-T DE-U GB-A

Years: 1836-2004

Patent/Publication No.: (JP61111340)

[no drawing available]

[Order This Patent](#)[Family Lookup](#)[Find Similar](#)[Legal Status](#)

[Go to first matching text](#)

**JP61111340 A****FLAME-RETARDANT POLYURETHANE FOAM****ASAHI CHEM IND CO LTD****Inventor(s): JOGO HIROYUKI ; MUTO MASARU****Application No. 59231344 JP59231344 JP, Filed 19841105, A1 Published 19860529**

**Abstract:** PURPOSE: To attain excellent flame retardance inexpensively, by forming a dry film of a compd. contg. a particular chlorine-contg. resin latex, fine-grain hydrous inorg. compd., and antimony oxide onto a polyurethane foam.

CONSTITUTION: 25W45wt%, in terms of resin solids, polyvinylidene chlorido resin latex with the chlorine content in the resin of 40W65wt% and/or vinyl chloride resin latex with the chlorine content in the resin of 40W54wt%, 50W70wt% one or more hydrous inorg. compds. with an average particle size of 20μ or below (e.g., aluminum hydroxide), and 0.5W10wt% antimony oxide with an average particle size of the primary particles of 0.5μ or less are mixed to prepare a compd. 50W230pts.wt. dry film of said compd. is adhered to 100pts. wt. polyurethane foam to yield the intended flame-retardant polyurethane foam.

COPYRIGHT: (C)1986,JPO&Japio

Int'l Class: C08J00942;

**Patents Citing this One:** No US, EP, or WO patents/search reports have cited this patent.



Home



Search



List

For further information, please contact:

[Technical Support](#) | [Billing](#) | [Sales](#) | [General Information](#)

**FLAME-RETARDANT POLYURETHANE FOAM**

**Patent number:** JP61111340  
**Publication date:** 1986-05-29  
**Inventor:** JOGO HIROYUKI; others: 01  
**Applicant:** ASAHI CHEM IND CO LTD  
**Classification:**  
**- international:** C08J9/42  
**- european:**  
**Application number:** JP19840231344 19841105  
**Priority number(s):**

**Abstract of JP61111340**

**PURPOSE:** To attain excellent flame retardance inexpensively, by forming a dry film of a compd. contg. a particular chlorine-contg. resin latex, fine-grain hydrous inorg. compd., and antimony oxide onto a polyurethane foam.

**CONSTITUTION:** 25-45wt%, in terms of resin solids, polyvinylidene chlorido resin latex with the chlorine content in the resin of 40-65wt% and/or vinyl chloride resin latex with the chlorine content in the resin of 40-54wt%, 50-70wt% one or more hydrous inorg. compds. with an average particle size of 20 $\mu$ m or below (e.g., aluminum hydroxide), and 0.5-10wt% antimony oxide with an average particle size of the primary particles of 0.5 $\mu$ m or less are mixed to prepare a compd. 50-230pts.wt. dry film of said compd. is adhered to 100pts. wt. polyurethane foam to yield the intended flame-retardant polyurethane foam.

---

Data supplied from the **esp@cenet** database - Worldwide